

OD 343

OD 34.29mm / 1.350inch

ID 23.37mm
HT 8.89mm



Core Dimensions

		OD(max)	ID(min)	HT(max)
Before coating	(mm)	34.29	23.37	8.89
	(inch)	1.350	0.920	0.350
After coating (Epoxy)	(mm)	35.20	22.60	9.83
	(inch)	1.385	0.888	0.387

Magnetic Dimensions

Cross Section (A)	Path Length (l)	Window Area (Wa)	Volume (V)
0.454cm ²	8.95cm	4.01cm ²	4.0633cm ³
0.0704in ²	3.53in	788,500cmil	0.2485in ³

Available Cores

MPP	Part No.		AL (nH/N ²)	Perm. (μ)
	High Flux	Sendust		
CM343026	CH343026	CS343026	16	26
CM343060	CH343060	CS343060	38	60
-	-	CS343075	47	75
-	-	CS343090	57	90
CM343125	CH343125	CS343125	79	125
CM343147	CH343147	-	93	147
CM343160	CH343160	-	101	160
CM343173	-	-	109	173
CM343200	-	-	126	200

Winding Information

AWG Wire		Single Layer		AWG Wire		Single Layer	
No.	Dia.(cm)	Turns	Rdc, Ω	No.	Dia.(cm)	Turns	Rdc, Ω
12	0.213	27	0.00533	21	0.0785	77	0.105
13	0.190	30	0.00740	22	0.0701	87	0.148
14	0.171	34	0.0102	23	0.0632	96	0.206
15	0.153	38	0.0143	24	0.0566	108	0.288
16	0.137	43	0.0199	25	0.0505	121	0.404
17	0.122	49	0.0277	26	0.0452	135	0.569
18	0.109	55	0.0388	27	0.0409	150	0.789
19	0.0980	61	0.0541	28	0.0366	168	1.11
20	0.0879	69	0.0754	29	0.0330	186	1.53

Single layer winding with 1 inch leads

AL vs NI Curve (60μ, 125μ)

