

OD 3.56mm / 0.140inch

ID 1.78mm
HT 1.52mm



Core Dimensions

		OD(max)	ID(min)	HT(max)
Before coating	(mm)	3.56	1.78	1.52
	(inch)	0.140	0.070	0.060
After coating (Parylene-C)	(mm)	3.76	1.58	1.72
	(inch)	0.148	0.062	0.068

Magnetic Dimensions

Cross Section (A)	Path Length (l)	Window Area (Wa)	Volume (V)
0.0137cm ²	0.817cm	0.018cm ²	0.010746cm ³
0.0021in ²	0.317in	3,600cmil	0.000656in ³

Available Cores

MPP	Part No.		AL (nH/N ²)	Perm. (μ)
	High Flux	Sendust		
-	-	-	-	26
CM035060	CH035060	CS035060	13	60
-	-	CS035075	16	75
-	-	CS035090	19	90
CM035125	CH035125	CS035125	26	125
CM035147	-	-	31	147
CM035160	-	-	33	160
-	-	-	-	173
-	-	-	-	200

Winding Information

AWG Wire		Single Layer		AWG Wire		Single Layer	
No.	Dia.(cm)	Turns	Rdc, Ω	No.	Dia.(cm)	Turns	Rdc, Ω
28	0.0366	9	0.0237	37	0.0140	27	0.363
29	0.0330	10	0.0314	38	0.0124	30	0.503
30	0.0294	11	0.0431	39	0.0109	35	0.727
31	0.0267	13	0.0581	40	0.0096	40	1.02
32	0.0241	14	0.0768	41	0.00863	44	1.37
33	0.0216	16	0.105	42	0.00762	50	1.90
34	0.0191	19	0.146	43	0.00685	56	2.67
35	0.0170	21	0.200	44	0.00635	60	3.45
36	0.0152	24	0.272				

Single layer winding with 1 inch leads

AL vs NI Curve(125μ)

