

The information contained in this drawing is the sole property of Coil Winding Specialist Inc (CWS).
Any reproduction in part or whole without written permission of CWS is prohibited.

T94-26

Features

Good results of general power conversion and line filter administration.
Applicable (at <50kHz) for Power Factor Correction Chokes, DC Chokes and lower Et/N.
Also applies for 60 Hz differential-mode EMI Line Chokes, and light dimmer chokes.

Electrical Specifications				
Item	Unit/Symbol	Condition	Value	Tol.
A _L	nH/N ²	AC flux density of 10 gauss (1 mT) @10 kHz	60.0	± 10%
L _e	cm	N/A	5.97	Typ.
A _e	cm ²	N/A	0.362	Typ.
V _e	cm ³	N/A	2.160	Typ.
Density	g/cm ³	N/A	7.0	Typ.
Permeability	μ ₀	N/A	75	± 10%
Permeability with DC BIAS	%μ ₀ , μ ₀ effective	HDC = 50 Oersted	51, 38.3	Typ.
Temp. Coef. of Permeability	+ppm/°C	N/A	825	Typ.
Coef. of Lin. Expansion	+ppm/°C	N/A	12	Typ.
Thermal Conductivity	mW/cm-°C	N/A	42	Typ.

$$\text{Temperature Rise : } \Delta T(^{\circ}\text{C}) = \left[\frac{\text{Total Power Dissipation (milliwatts)}}{\text{Surface Area (cm}^2\text{)}} \right]^{0.833}$$

$$\text{Required turns} = \left[\frac{\text{desired L (nH)}}{A_L \left(\frac{nH}{N^2} \right)} \right]^{\frac{1}{2}}$$


$$\text{Peak AC Flux Density: } B_{pk} = \frac{E_{avg} 10^8}{4ANf}$$

$$\text{Magnetizing Force: } H = \frac{0.4\pi NI}{\ell}$$

L = inductance
nH = nanohenries
H = oersteds (Oe)
N = Number of turns
I = Current (amperes)
ℓ = Mean Magnetic Path (cm)
A = Cross-sectional area (cm²)
f = frequency (hertz)
B_{pk} = Gauss (G)

Core Loss in mW/cm ³ (extrapolated data from high frequency testing)						
Frequency	60 Hz	1kHz	10kHz	50kHz	100kHz	500kHz
Condition	@ 5000G	@ 1500G	@ 500G	@ 225G	@ 140G	@ 50G
Value	32	60	75	89	83	139

REVISION HISTORY						
REV	ECN	DESCRIPTION	SIGN & DATE			
			BY	DATE	AP.	DATE
A		Production release	EO	3/7/13	JL	3/7/13



Case Dimensional Tolerances				
	in	tol.	mm	tol.
B (Outer Diameter)	0.942	0.020	23.90	0.51
A (Inner Diameter)	0.560	0.020	14.20	0.51
H (Height)	0.312	0.025	7.92	0.64
Weight	15.12 g			

For additional detail, specifications and charts see:

http://www.bytemark.com/products/IPCores_index.html

CODE IDENT		MFG. P/N	DESCRIPTION		ITEM NO.
PARTS LIST					
AUTOCAD		X		CWSBYTEMARK 353 West Grove Ave. Orange, CA. 92865	
SOLIDWORKS					
SIGN		DATE		www.coilws.com www.cwsbytemark.com	
DRAWN		EO 3/7/13		TITLE: Iron Powder Core Material Mix 26, Yellow/White	
CHECKED		JL 3/7/13			
ENGR.		JL 3/7/13			
APPR.		JL 3/7/13			
		SIZE DWG. NO.			REV
		B T94-26			A
		SCALE N/A			SHEET 1 OF 1