F-114-43

## REVISION HISTORY REV ECN DESCRIPTION SIGN & DATE BY DATE AP. DATE A Production release EO 1/31/13 JL 1/31/13


## **Features**

NiZn ferrite with a range of 20 to 250 MHz for suppression of conducted EMI, that is used for inductive applications (ex: high frequency common-mode chokes)

Burnished to break sharp edges, can contain Parylene C coat at smaller diameters from length 9.5mm (0.375") or a uniform coating of thermo-set plastic for larger dimension (if part numbers ends with a C).

Electrical Specifications								
Item	Unit/Symbol	Condition	Value	Tol.				
$A_{L}$	nH/N <sup>2</sup>	@ 10 KHz	510	± 20%				
Le	cm	N/A	7.3	± 10%				
Ae	cm <sup>2</sup>	N/A	0.37	± 10%				
V <sub>e</sub>	cm <sup>3</sup>	N/A	2.7	± 10%				
Initial Permeability	$\mu_0$	@ B < 10 gauss	800	± 20%				
Temp. Coeff. Of initial Permeability	%, °C	%, °C 20 - 70 °C		Тур.				
Coercive Force	H <sub>c</sub>	oersted	0.45	Тур.				
Residual Flux Density	Gauss, Br	N/A	1300	Тур.				
Flux Density	Gauss, B	Initial (B), oersted	2900	Тур.				
	Gauss, H	@ Field Strength (H), oersted	10	Тур.				
Curie temperature	°C	T <sub>c</sub>	> 130	Nom.				
Resistivity	Ω cm, ρ	@ Field Strength	10 <sup>5</sup>	Тур.				
Loss Factor	$10^{-6}$ , tan $\delta$ / $\mu$	Initial	250	Тур.				
	MHz	@ Frequency	1	Тур.				

Dimensional Tolerances							
	in	tol.	mm	tol.			
Case							
B (Outer Diameter)	1.142	± 0.026	29.00	± 0.65			
A (Inner Diameter)	0.748	± 0.020	19.00	± 0.50			
H (Height)	0.295	± 0.010	7.50	± 0.25			
Weight 13.00 g							



## For additional detail, specifications and charts see:

http://www.bytemark.com/products/ferrite\_matl.htm

			CODE MFG		s. P/N	DESCRIP		ION	ITEM NO.	
		PARTS LIST								
		AUTOCAD X				CWSBYTEMARK				
		SOLID	VORKS		www.coilws.com		353 West Grove Ave. Orang			
	UNLESS OTHERWISE SPECIFIED	SI	GN	DATE	www.cwsb	www.cwsbytemark.com	92865		Jiange, CA.	
	DIMENSIONING AND TOLERANCE PER ANSI Y14.5M	DRAWN	ЕО	1/31/13	TITLE:	rrita Tarai	d Coro			
	ALL DIMENSIONS ARE IN INCHES AND [MILIMETERS].	CHECKED	JL	1/31/13	Ferrite Toroid Core Material 43, NiZn					
	TOLERANCE INCHES: .XXX=±.005 .XX=±.015 ◀=±0'30' TOLERANCE METRICS:	ENGR.	JL	1/31/13	CITE INVA U	43,	MIZII			
.XXX=±.127 .X	XXX=±.127 .XX=±.38 <=±0'30'  ANGLE PROJECTION	APPR.	JL	1/31/13	SIZE DWG. NO.	F-1	14-43		REV A	
	DO NOT SCALE DRAWING				SCALE	N/A		SHEET 1 O	F 1	

EP FORMO005 REV 3 10/01 CAD-FILE: